

ENGRAVE-A-CRETE, INC.

Technical Data Sheet (TDS) CR-515 INSIDE ACRYLIC

Product

CR-515 is a low odor, non-yellowing, water-based acrylic sealer for concrete floors that provides slightly deeper color appearance along with a low gloss finish for interior concrete. CR-515 Inside Acrylic has excellent water and efflorescent resistance and superior durability. It has strong UV resistance and adhesion to a wide variety of substrates and it will not chalk or yellow.

Coverage

First Coat: 250-350 square feet per gallon.

Optional Second Coat: 350-400 square feet per gallon.

Coverage variations occur based on concrete surface porosity and amount of material applied.

Surface Preparation

Concrete must be clean and free of dirt, dust, oil, grease, mold and mildew, and any other contaminants.

RAC Stained concrete must be neutralized, thoroughly cleaned, and dry prior to sealing.

WRC Stained concrete must be completely cured prior to sealing.

All new concrete should be allowed to cure for a minimum of 45 days, or until a pH reading of 10.5 or less is achieved. Concrete must be completely dry prior to sealer application. It is strongly recommended that a surface probe moisture meter be utilized to verify the surface is dry. After visually determining the concrete is dry, test a minimum of 10 different areas of the concrete with the moisture meter. Pay special attention to cracks, control joints, and slab edges.

Application Recommendations

ROLLER

Stir well before use. Pour CR-515 Inside Acrylic through a strainer prior to use. Apply by using a high quality 3/8" nap lint free roller cover, or 1/4" nap mohair roller cover (for smooth surfaces). Dip directly into a roller pan and distribute the material by rolling laterally and then up and down (crosshatch rolling). Roll the material into a wet edge, and avoid excessive back rolling. When applying 2 coats of sealer roll the second coat perpendicular to the first. Keep containers closed when not in use, unattended open material will form a skin on the surface.

SPRAYER – HVLP or Airless

Stir well before use. Pour CR-515 Inside Acrylic through a strainer prior to use. Spray Inside Acrylic using an airless or HVLP spray system. Do When applying 2 coats, spray the second coat perpendicular to the first.

Always use a chemical respirator when spraying with an airless or HVLP spray system. Keep containers closed when not in use, unattended open material will form a skin on the surface.

Thinning - Do not thin CR-515 Inside Acrylic

Drying Time

Dry to touch: 30 minutes

Dry hard: 55 minutes

Recoat: 2 hours

Light Foot Traffic: 4 hours

Full Cure: 72 hours

The listed dry times are for 75 degree (F) temperatures and medium humidity. Low temperatures and/or high humidity will slow drying and curing time.

Clean Up - Tools can be cleaned with soap and water.

Storage and Shelf Life

Do not allow to freeze. Shelf life of unopened product is approximately one year.

Limitations

Not suitable for flooring that is exposed to harsh chemicals. In high traffic areas a maintenance coat of CR-520 Inside Floor Finish is required.

Air and substrate temperatures must be minimum 50 degrees (F). Do not apply when air or surface temperature exceeds 90 degrees (F) or LAP marking / poor penetration / bubbling may result.

Do not apply to wet or damp concrete, moisture will inhibit penetration of the sealer and cause improper curing, flaking or lifting of the sealer.

Do not apply if dew may condense on the surface before the sealer has cured. Allow for extended dry times during cold weather / high humidity.

Slip and Fall Precautions

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slip-resistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. Concrete Stain & Supply, LLC recommends the use of angular slip-resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. Concrete Stain & Supply, LLC or its sales agents will not be responsible for injury incurred in a slip and fall accident.

Moisture Vapor Emissions/Alkalinity Precautions

All interior concrete floors not poured over an effective moisture vapor barrier/inhibitor are subject to possible moisture vapor transmission and related high levels of alkalinity that may lead to blistering and failure of the coating system. It is the coating applicator's responsibility to conduct calcium chloride and relative humidity probe testing to determine if excessive levels of vapor emissions or alkalinity are present before applying any coatings.

Warranty– This warranty is made in lieu of all other warranties, either expressed or implied. Before application the User shall determine the suitability of the product for his/her intended use and User assumes all risks and liabilities whatsoever in connection therewith. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The Manufacturer and/or Seller warrants that if any goods supplied prove defective in material the sole obligation shall be to replace said product. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither Manufacturer nor Seller shall assume any liability for injury, loss, or damage resulting from use of this product.

Ordering – Contact Engrave-A-Crete at 1-800-884-2114

• www.ConcreteResurrection.com • www.Engrave-A-Crete.com